

Chongqing Polycomp International Corp.

Jianqiao Industiral Park B, Dadukou District Chongqing, China.

Post code: 400082 website: www.cpicfiber.com

Technical support . Tel: (+86-23)68157743 (+86-23)68157178

Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586

Fax: (+86-23)68157822


Woven Roving EWR600-960/1000/1270

Identification

Example: EWR600-1000

EWR: E-Glass Woven Roving **600:** Area weight (g/m²)

1000: Width (mm)



Product Description

The Woven Roving fabrics are made from Direct Rovings. They are widely used in marine, rail transportation and mostly applied in hand lay-up process

Product Benefits

- Rapid wet through and wet out.
- · High mechanical strength.
- · Compatible well with polyester, epoxy resin

Technical Characteristics

Sizing type	Area Weight (g/m2)		nread count (/cm) Wid		(mm)	Loss on Ignition (%)	Moisture Content (%)
/	ISO 3374	ISO 4602		ISO 5025		ISO 1887	ISO 3344
Ciloro	.50/	Warp	±0.20	<600	±5	0.00.000	<0.45
Silane	±5%	Weft	±0.20	≥600	±10	0.30~0.80	≤0.15

Product code	Glass type	Weave	Warp (Tex)	Weft (Tex)	Thread count (/cm)	Weight (g/m2)	Width (mm)
EWR600-960	E*	Plain	1200	1200	2.50 x 2.30	600	960
EWR600-1000	E*	Plain	1200	1200	2.50 x 2.30	600	1000
EWR600-1270	E*	Plain	1200	1200	2.50 x 2.30	600	1270

^{*}E/ECR/ECT glass types are available.



Chongqing Polycomp International Corp.

Jianqiao Industiral Park B, Dadukou District Chongqing, China.

Post code: 400082 website: www.cpicfiber.com

Technical support . Tel: (+86-23)68157743 (+86-23)68157178


Marketing Dept. Tel: (+86-23)68157828 (+86-23)681577586

Fax: (+86-23)68157822

Packaging

Package	Core Inside/Outside Diameter(mm)	General Length (m/roll)	Roll Wight(kg/roll)	Number of roller per pallet	Pallet size(mm) L*W*H
EWR600- 960	88.5/260	105	60	12/16	1070*1120*140
EWR600- 1000	88.5/260	105	63	12/16	1070*1120*140
EWR600- 1270	88.5/260	105	80	12/16	1350*1120*140

Pallets illustration



Note: Fabrics can be packed according to the customer's request.

Storage

The fabrics should be stored away from heat and moisture, and in their original packaging. The best conditions are: temperatures between 15 and 35 °C; humidity between 35 and 65 %

If the product is not stored under these specifications, it is advisable to condition it in the workshop for at least 24 hours before use, to prevent condensation.

CPIC recommends that the material be used according to FIFO (first in, first out) method. It is recommended the use of a spacer plate (10mm) between the pallets.







ISO 9001

ISO 14001

OHSAS 18001